

Abstract

Good adhesion between layers is achieved in a multilayer composite having the following layers:

- I. a layer I of a polyamide molding composition;
- II. a layer II of a bonding agent having at least 50% by weight of a mixture of
 - a) from 30 to 70 parts by volume of a polymer selected from
 - a polyamide and
 - a polyamine-polyamide copolymer,
 - b) from 0.1 to 70 parts by volume of an olefin polymer containing a functional group,
 - c) from 69.9 to 0 parts by volume of an unfunctionalized polyolefin, where the sum of the parts by volume of a), b) and c) is 100; and
- III. a layer III of a polyolefin molding composition.

I:\user\KGRUN\215747.pa.wpd